

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 MyDay® daily disposable	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform® Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay® toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	— —	Toric	Optimized Toric Lens Geometry™	Daily wear; 1 day replacement	8.6	14.5	0.100	Aquaform® Technology	stenfilcon A	54	80	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay® multifocal	-12.00 to -10.50 (0.50 steps) -10.00 to +8.00 (0.25 steps)	— —	— —	Low (+0.75 to +1.25 spectacle add) Med (+1.50 to +1.75 spectacle add) High (+2.00 to +2.50 spectacle add)	Multifocal	Binocular Progressive System™	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform® Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MyDay Energys®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	DigitalBoost®	Daily wear; 1 day replacement	8.4	14.2	0.080	Aquaform® Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 clariti® 1 day sphere	-10.00 to -6.50 (0.50 steps) -6.00 to -0.50 (0.25 steps) +0.50 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	— —	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
 clariti® 1 day toric	-9.00 to -6.50 (0.50 steps)	-0.75 -1.25 -1.75 10, 20, 60, 70, 80, 90, 100, 110, 120, 160, 170, 180	— —	-2.25 10, 20, 90, 160, 170, 180	Toric	Smooth-gradient ballast toric design	Daily wear; 1 day replacement	8.6	14.3	0.105	WetLoc® Technology	somofilcon A	56	57	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
clariti® 1 day Multifocal (3 add)	+0.25 to +4.00 (0.25 steps)	-0.75 -1.25 -1.75 10, 20, 70, 80, 90, 100, 110, 160, 170, 180	— —	— —	Multifocal	Binocular Progressive System™	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
clariti® 1 day multifocal	-6.00 to +5.00 (0.25 steps)	— —	— —	Low: Up to +1.25 High: +1.50 to +2.25	Multifocal	— —	Daily wear; 1 day replacement	8.6	14.1	0.070	WetLoc® Technology	somofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Live® daily disposable	10.00 to -6.50 (0.50 steps) -6.00 to -0.50 (0.25 steps) +0.50 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	— —	Daily wear; 1 day replacement	8.6	14	0.070	WetLoc® Technology	soofilcon A	56	86	0.5	66% UVA & 95% UVB; Class 2	No	5B (SiHy)
 MyDay® MiSight® 1 day	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	— —	— —	Treatment zones offer +2.00D of myopic defocus	Dual-focus	ActivControl® Technology	Daily wear; Recommendation to wear the lenses for a minimum of 10 hours per day for at least 6 days per week [§] ; 1 day replacement	8.4	14.2	0.080	Aquaform® Technology	stenfilcon A	54	100	0.4	87% UVA & 97% UVB; Class 2	Yes	5B (SiHy)
 MiSight® 1 day	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	— —	— —	Treatment zones offer +2.00D of myopic defocus	Dual-focus	ActivControl® Technology	Daily wear; Recommendation to wear the lenses for a minimum of 10 hours per day for at least 6 days per week [§] ; 1 day replacement	8.7	14.2	0.090	PC Technology® (phosphoryl choline)	omafilcon A	60	28	JAPAN ONLY Dk/t=22.8 (due to boundary corrected Dk test method for RA approval)	No	Yes	2
 Proclear® 1 day	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 1 day replacement	8.7	14.2	0.090	PC Technology® (phosphoryl choline)	omafilcon A	60	28	0.3	No	Yes	2
 Proclear® 1 day multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to +6.00 (0.25 steps)	— —	— —	Single power profile +1.50D (Could fit adds up to +2.50)	Multifocal	— —	Daily wear; 1 day replacement	8.7	14.2	0.090	PC Technology® (phosphoryl choline)	omafilcon A	60	28	0.3	No	Yes	2

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Biomedics® 1 day Extra	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO	— —	— —	— —	Spherical optic (sphere)	— —	Daily wear; 1 day replacement	8.6	14.2	0.075	— —	ocufilcon D	55	26	0.5	No	Yes	4
	+6.00 to +0.25 (0.25 steps) NO PLANO	— —	— —	— —				8.8										
 Biomedics® 1 day Extra toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps)	-0.75, -1.25, -1.75	10 to 180 (in 10 steps)	— —	Toric	Optimized Toric Lens Geometry™	Daily wear; 1 day replacement	8.7	14.5	0.109	— —	ocufilcon D	55	18	0.5	No	Yes	4

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] ($\text{D} - 3.00\text{DS}$) $\times 10^{-9}$ [(cm/sec) \times (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Biomedics®, clariti®, CooperVision®, live®, MyDay®, MyDay Energys®, MiSight® and Proclear® are registered trademarks of The Cooper Companies, Inc. and its subsidiaries.

©2026 CooperVision SA09487 Rev. #8 01/2026

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Biofinity®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement Extended wear; 7 days/6 nights; 30 day replacement	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity® XR	-20.00 to -12.50 (0.50 steps) +8.50 to +15.00 (0.50 steps)	— —	— —	— —	Asphere	Aberration Neutralizing System™	As for Biofinity sphere	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity Energys®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Digital Zone Optics® (Use DigitalBoost® technology only for markets where MyDay Energys® has been launched)	As for Biofinity sphere	8.6	14	0.075	Aquaform® Technology	comfilcon A	48	171	0.6	No	Yes	5C (SiHy)
 Biofinity® toric	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	— —	Toric	Optimized Toric Lens Geometry™	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] $(@-3.00DS) \times 10^{-9} [(\text{cm/sec}) \times (\text{ml O}_2) / (\text{ml} \times \text{mmHg})]$

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Biofinity® XR Toric	-20.00 to -10.50 (0.50 steps) +8.50 to +20.00 (0.50 steps)	-0.75 -1.25 -1.75 -2.25	5 to 180 (5 steps)	— —	Toric	Optimized Toric Lens Geometry™	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)
 Biofinity® multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	— —	— —	+1.00 +1.50 +2.00 +2.50	Multifocal D lens N lens	Balanced Progressive® Technology	As for Biofinity sphere	8.6	14	0.090 to 0.110 (add dependant)	Aquaform® Technology	comfilcon A	48	142 (-3.00, N lens, +1.00 Add)	0.6	No	Yes	5C (SiHy)
 Biofinity® toric multifocal	-10.00 to -6.50 (0.50 steps) -6.00 to plano (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50D to +10.00 (0.50 steps)	-0.75 to -5.75 (0.50 steps)	5 to 180 (5 steps)	+1.00 +1.50 +2.00 +2.50	Toric Multifocal Aspheric FS-D Lens N lens	Optimized Toric Lens Geometry™ Balanced Progressive® Technology	As for Biofinity sphere	8.7	14.5	0.110	Aquaform® Technology	comfilcon A	48	116	0.6	No	Yes	5C (SiHy)
 Avaira Vitality®	-12.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +6.00 (0.25 steps) +6.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement Daily wear; 2 weekly replacement - US, Australia, Italy, selectively in France	8.4	14.2	0.080	Aquaform® Technology	fanfilcon A	55	112	0.5	93% UVA & 100% UVB; Class 1	Yes	5B (SiHy)

* Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Avaira Vitality® toric	-10.00 to -6.50D (0.50D steps) -6.00 to -plano (0.25D steps) +0.25 to +6.00D (0.25D steps) +6.50 to +8.00D (0.50D steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	— —	Toric	Optimized Toric Lens Geometry™	Daily wear; 30 days replacement Daily wear; 2 weekly replacement -US, Australia, Italy, selectively in France	8.5	14.5	0.100	Aquaform® Technology	fanficon A	55	90	0.5	93% UVA & 100% UVB; Class 1	Yes	5B (SiHy)
 Proclear®	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) NO PLANO -20.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.50 to +6.00 (0.25 steps) +6.50 to +20.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	— —	Daily wear; 30 days replacement	8.2	14.2	0.075	PC Technology® (phosphoryl choline)	omafilcon B	62	36	0.4	No	Yes	2
 Proclear® toric	-8.00 to -7.00 (0.50 steps) -6.50 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	— —	Toric	— —	Daily wear; 30 days replacement	8.4 (MTO) 8.8 (MTO or moulded)	14.4	0.138 0.114	PC Technology® (phosphoryl choline)	omafilcon B	62	16 (MTO) 19.4 (MTO) 23.7 (Moulded)	0.4	No	Yes	2
 Proclear® XR toric	-10.00 to -7.00 (0.50 steps) -6.50 to Plano (0.25 steps) +0.25 to +6.50 (0.25 steps) +7.00 to +10.00 (0.50 steps)	-0.75 to -5.75D (0.50D steps)	5 to 180 (5 steps)	— —	Toric	— —	Daily wear; 30 days replacement	8.4	14.4	0.212	PC Technology® (phosphoryl choline)	omafilcon B	62	10.4 13.9	0.4	No	Yes	2

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] $(@-3.00DS) \times 10^{-9} [(cm/sec) \times (ml O_2)/(ml \times mmHg)]$

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis [°]	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Proclear® multifocal	-8.00 to -7.00 (0.50 steps) -6.50 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	— —	— —	+1.00 +1.50 +2.00 +2.50	Multifocal D lens N lens	— —	Daily wear; 30 days replacement	8.7	14.4	0.157 to 0.161 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	14 (MTO)	0.4	No	Yes	2
 Proclear® XR multifocal	-20.00 to -7.00 (0.50 steps) -6.50 to Plano (0.25 steps) +0.25 to +6.50 (0.25 steps) +7.00 to +20.00 (0.50 steps)	— —	— —	+1.00 to +4.00 (0.50 steps)	Toric Multifocal D lens N lens	— —	Daily wear; 30 days replacement	8.4	14.4	0.060 to 0.113 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	From: 14.0 (-3.00D/ +4.00D, N Type) To: 16.7 (-3.00D/ +2.50D, D type)	0.4	No	Yes	2
 Proclear® multifocal toric	-20.00 to -7.00 (0.50 steps) -6.50 to Plano (0.25 steps) +0.25 to +6.50 (0.25 steps) +7.00 to +20.00 (0.50 steps)	-0.75 to -5.75 (0.50 steps)	5 to 180 (5 steps)	+1.00 to +4.00 (0.50 steps)	Toric Multifocal D lens N lens	— —	Daily wear; 30 days replacement 2 weekly replacement US	8.4	14.4	0.060 to 0.115 (add dependant)	PC Technology® (phosphoryl choline)	omafilcon B	62	From: 14.5 (-3.00D/ +4.00D, N Type) To: 17.7 (-3.00D/ +4.00D, D Type)	0.4	No	Yes	2
 Biomedics® 55 Evolution [Biomedics 55 UV Asphere]	-10.00 to -6.50 (0.50 steps) -6.00 to -0.25 (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement 2 weekly replacement US EU/CE mark markets (ANZ): Extended wear 7 days/6 nights; 30 day replacement (NOT IN EU/ANZ after 26 May 2024)	8.6, 8.8, 8.9	14.2	0.075	— —	ocufilcon D	55	26	0.4	69% UVA & 97% UVB; Class 2	Yes	4

^{*} Plano lens availability for sphere product can vary by market or customer.

[†] $(@-3.00DS) \times 10^{-9} [(cm/sec) \times (ml O_2)/(ml x mmHg)]$

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. CL wearers should continue to use UV-absorbing eyewear as directed by their eye care professional.

[§] Wearing schedule for best results.

Product specifications

To learn more about our contact lenses visit:
[Regional/Country CooperVision URL](#)



Product	Sphere Power (DS) [*]	Cylinder Power (DC)	Axis°	Add Power (D)	Design	Design Technology	Wear Schedule & Replacement Frequency	Base Curve (mm)	Diameter (mm)	Centre thickness (ct, mm)	Material Technology	Material USAN	Water content (%)	Oxygen transmissibility Dk/t [†]	Modulus (MPa, tested with -1.00DS lenses)	UV Blocking (% tested with -3.00DS lenses) & Class [‡]	Visibility Tint	FDA Group
 Biomedics® Now (Sphere) (Only sold in Greece in EU; No longer sold in EU after 26 May 2024)	-10.00 to -6.50 (0.50 steps) -6.00 to -.025. (0.25 steps) +0.25 to +5.00 (0.25 steps) +5.50 to +8.00 (0.50 steps) NO PLANO	— —	— —	— —	Asphere	Aberration Neutralizing System™	Daily wear; 30 days replacement 2 weekly replacement US EU/CE mark markets (ANZ): Extended wear 7 days/6 nights; 30 day replacement (NOT IN EU/ANZ after 26 May 2024)	8.6	14.2	0.075	— —	ocufilcon D	55	26	0.4	69% UVA & 97% UVB; Class 2	Yes	4
 Biomedics® toric	-10.00 to -6.50 (0.50 steps) -6.00 to Plano (0.25 steps) +0.25 to +6.00 (0.25 steps)	-0.75 -1.25 -1.75 -2.25	10 to 180 (10 steps)	— —	Toric	Optimised Toric Lens Geometry™	Daily wear; 30 days replacement EU/CE mark markets (ANZ): Extended wear 7 days/6 nights; 30 day replacement (NOT IN EU/ANZ after 26 May 2024)	8.7	14.5	0.109	— —	ocufilcon D	55	18	0.4	69% UVA & 97% UVB; Class 2	Yes	4

* Plano lens availability for sphere product can vary by market or customer.

[†] (@-3.00DS) x 10⁻⁹ [(cm/sec) x (ml O₂)/(ml x mmHg)]

[‡] UV-blocking contact lenses help provide protection against transmission of harmful UV radiation to eye but are not substitutes for protective UV-absorbing eyewear, such as UV-absorbing goggles or sunglasses, as they do not completely cover the eye or surrounding area. Continue to use UV-absorbing eyewear as directed by your eye care professional.